



# MIRROR GLOSS

GLOSS FINISH FOR INTERIOR AND EXTERIOR

PRODUCT INFORMATION	
PRODUCT NAME	Mirror Gloss Finish
PRODUCT CODE	D104 (Solventborne)
DESCRIPTION	<b>Mr. Paint Man</b> Mirror Gloss Finish is a high gloss finish for interior and exterior.
USAGE	For new or previously painted interior and exterior wood (doors, windows, fascias) and metal (grilles, gates) surfaces, where a tough, durable, high gloss finish is required.
BENEFITS	Gives a tough, mirror-like high gloss finish and has excellent weathering and fungus resistance.
PACK SIZE	0.9 and 4.5 Litres.
COLOR RANGE	Refer to <b>Mr. Paint Man</b> Emotion of Colours.

PERFORMANCE GUIDE	
FILM PROPERTIES	
Chemical Resistance	Resistant to mild chemical fume attack but where there is heavy attack, e.g. actual contact with chemicals, specialist paint systems will be required.
Heat Resistance	Generally resistant to heat up to 90°C, but some discolouration of light colours may occur at temperatures above 80°C.
Water Resistance	Resistant to the atmospheric humidity levels present in normal interior and exterior environments and will withstand repeated washing. Not suitable for use on immersed surfaces.
THEORETICAL COVERAGE	Approximately 12 - 15m <sup>2</sup> /litre @ 30 microns DFT
No. of Coats	2 or more for best result

PRODUCT DATA	
COMPOSITION (nominal)	
Pigment	Lightfast Non-Lead Pigments.
Binder	Alkyd.
Solvent	White Spirit.

APPLICATION	
THINNING	
Brush or Roller	For normal use, thinning is usually not necessary. If required, should not exceed 1 part of mineral turpentine to 10 parts of paint (10%).
Conventional Spray	Add up to 1 part of mineral turpentine to 3 parts of paint (30%)

## Mr. Paint Man MIRROR GLOSS

Airless Spray	Ready for use.
<b>SPRAY RECOMMENDATIONS</b> Conventional Spray Airless Spray	Satisfactory through most equipment. A typical set up for airless spray application would be a minimum working pressure on paint of 140Kg/cm <sup>2</sup> (2000 lb/sq in) with a spray tip size 0.38mm(15 thou) and a spray tip angle of 65°
Drying Times Touch Dry Recoat	Single coat at standard thickness : Dependant on temperature and humidity. 6 – 8 hours.
<b>CLEANING UP</b>	Immediately with mineral turpentine.

## PRE-APPLICATION

<b>SURFACE PREPARATION AND SYSTEM INFORMATION</b>	<p>For new unpainted metal, remove rust and use mineral turpentine to remove all grease, oil and wax. Prime the surface with <b>Mr. Paint Man 'Metal Anti Rust Primer'</b>. For new, unpainted wood, ensure surfaces are clean, dry and free from grease, oil and wax. Use a suitable Aluminium Wood Primer for highly resinous wood and for a better finish after priming; apply 1 coat of <b>Mr. Paint Man 'MG Wood Undercoat'</b>.</p> <p>When repainting metal and wood, thoroughly sand down using a suitable abrasive paper. Remove all rust, grease, wax and surface contaminants. For exposed metal, use <b>Mr. Paint Man 'Metal Anti Rust Primer'</b> and for wood, apply a coat of <b>Mr. Paint Man 'MG Wood Undercoat'</b>.</p> <p><b>Mirror Gloss</b> is also suitable for use on properly prepared masonry surfaces where a high gloss finish is required.</p>
---	---

## PRECAUTION

<b>SAFETY MEASURES AND INSTRUCTIONS</b>	<p>Keep container tightly closed. Keep out of reach of children. When applying paint, it is advisable to wear eye protection. In case of contact with eyes, rinse immediately with water and seek medical assistance.</p> <p>To remove splashes of paint from skin, use soap and water. In the event of spillage, contain and collect spillage using sand or soil. Do not empty into drains or water courses.</p> <p>Chemical Safety Data Sheet (CSDS) is available upon request.</p>
---	---

For further details, kindly contact:

**MR. PAINT MAN SDN BHD** (649192-U)

No. A-30-06, 3-Two Square, No. 2 Jalan 19/1,  
46300 Petaling Jaya, Selangor Darul Ehsan, Malaysia.

Tel: 603 7960 8199 Fax: 603 7960 9399

As errors and omissions may occur, any advice, information, assistance provided by Mr. Paint Man Sdn Bhd regarding goods manufactured or their use or any application is not subject to any, expressed or implied, warranties.